

1° Istituto Italiano di ricerca, collaudo, test e certificazione di calzature, abbigliamento dispositivi di protezione individuale per il lavoro, lo sport, e l'outdoor

The 1st Italian testing and research center for footwear, clothing, Personal Protective Equipment and Outdoor Sports Equipment

1. Italienisches Prüf- und Forschungsinstitut für Schuhe, Bekleidung, Persönliche Schutzausrüstung und Outdoor Sportausrüstung

SR Firm: KTM MOTORCYCLE AG

Stalhofnerstraße, 3 5230 Mattighofen Austria

Ausii

DC 9723 For the attention of: Gabriele Debettio

TEST REPORT

RAPPORTO DI PROVA

PRÜFBERICHT

N. **3724080/E**

date:

05/09/2018

Sampling: done by the Applicant

Samples received on:

13/07/2018

Test period: 07/08-05/09/2018

ORGANISMO NOTIFICATO N. 0498 Tutti i risultati si riferiscono esclusivamente ai materiali esaminati.

Vietata la riproduzione parziale o la pubblicazione, ad es. a scopo pubblicitario, senza autorizzazione scritta di RCT.

L'esito positivo di un rapporto di prova non implica che il prodotto sia "approvato" o "certificato" da RCT.

Commenti e dichiarazioni sono di natura soggettiva e non fanno parte del RdP. # Prova eseguita da laboratorio partner aualificato.

NOTIFIED BODY N. 0498

All results refer exclusively to the tested materials.

Partial reproduction or publication, e.g. for advertising purpose not admitted without written authorization by RCT.

Positive results of a test report do not imply that the tested product is "certified" or "approved" by RCT.

Comments and interpretations are of subjective nature and not part of the Test Report.

Test carried out by qualified partner lab.

NOTIFIZIERTE STELLE N. 0498

Alle Ergebnisse beziehen sich nur auf die geprüften Materialen. Partielle Reproduktion oder Veröffentlichung, z.B. zu Reklamezwecken,

ist nicht gestattet ohne schriftliche Zustimmung von RCT. Positive Ergebnisse eines Prüfberichtes bedeuten keine Homologierung oder Zottfisionung der Brodukts durch BCT.

Zertifizierung des Produkts durch RCT. Kommentare und Erklärungen sind subjektiver Natur und nicht Teil des Prüfbericht.

Test durchgeführt von qualifiziertem Partner-Labor.

SAMPLES: Jackets for motorcycling use declared class AA:

- art. "ADV S JACKET MEN" color black size M;

- art. "ADV S JACKET WOMAN" color black/grey/purple size S;

Trousers for motorcycling use declared class AA: - art. "ADV S PANTS MEN" color black size M:

- art. "ADV S PANTS WOMEN" color black/grey/purple size S;

See the complete description on the next page.

REQUEST: Laboratory tests in accordance with EN ISO 13688:2013 and FprEN

17092-3:2018 (version 2018-05) after 5 washing cycles (EN ISO 6330:2012) procedure 3G, drying procedure A for the aim of the Certification

(Regulation (EU)2016/425)

OUTCOME: O PASS

1 / 22



N. **3724080/E** date: 05/09/2018

NOTE:

Partial report – it does not contain the results of the following components, which have been previously tested:

- material 1a Report n.3716040/E for tear strength;
- material 2 Report n.3714043/E material 3 for tear strength and DAM;
- material 3 Report n.3714043/E material 4 for tear strength and DAM Report n.3724078/E material 3 for pH and azo;
- material 4 Report n.3724078/E material 4 for pH and azo;
- material 6 Report n.3724078/E material 6 for pH and azo;
- material 7 Report n.3724078/E material 7 for pH and azo;
- material 8 Report n.3714043/E material 5 for tear strength and Report n.362003.01/E material 6 for pH and azo;
- material 9 Report n.362003.01/E material 10 for pH and azo and Report n. 3724078/E material 9 for tear strength;
- material 10 Report n.362003.01/E material 8 for pH and azo;
- material 12 Report n.3724079/E material 5 for pH and azo;
- material 13 Report n.362003.01/E material 9 for pH and azo;
- nickel release Report n.3724081/E;

Combination for DAM:

A/F) see Report n. 3714043/E material 3;

B/E) see Report n.362003.01/E combo A;

C) see Report n.3714043/E material 4;

D) see Report n.3709023/E combo C;



N. **3724080/E** date: 05/09/2018

Description:

article: "ADV \$ JACKET MEN" color black size M;

external side:

- black fabric "#4707 C2L C6 DWR" (1a);
- black leather "FIRARMINGO SOFT LEATHER" (2);
- black Velcro (4);
- black knitting "P2M 320 MESH/BLK" (3)

internal side:

- black felt "180G ALOVA AGAIST PEEING/BLK" (6);
- black fabric "#1206 330D TASLAN" (7);
- black perforated knitting "POLY 11:1 MESH" (8);
- orange knitting "CH-1068 FABRIC" (10);
- black tape "READY TO RACE" (11);
- black fabric "210T TAFFETA 4000 PU" (12);
- black fabric "210T TAFFETA P/D" (13);

removable lining:

- black knitting "1*1 POLY KNIT/BLK" (15);
- black fabric "420T TAFFETA PD/BLK" (16) matched with white material;
- black fabric "210T TAFFETA P/D" (13);
- black felt "180G ALOVA AGAIST PEEING/BLK" (6);

main fastening system:

- by means of a metallic zipper;

sleeve and wrist closure:

- metallic zipper;

external pockets:

- black fabric "210T TAFFETA 4000 PU" (12) with Velcro closure;

internal pockets:

- black fabric "210T TAFFETA 4000 PU" (12) with metallic zipper;

protectors pocket:

- for shoulder and elbow pockets: black perforated knitting "POLY 11:1 MESH" (8) with Velcro closure;
- for back protector pocket: black perforated knitting "POLY 11:1 MESH" (8) and black elastic knitting "PKT MOCK-UP" (9) with Velcro closure;

vents:

- black knitting "P2M 320 MESH/BLK" (3) with metallic zip closure;

article: "ADV \$ JACKET WOMAN" color black/grey/purple size \$;

it differs from model "ADV \$ JACKET MEN" color black size M in the following features:

<u>external side</u>:

- black fabric "#4707 C2L C6 DWR" (1a);
- gray fabric "#4707 C2L C6 DWR 7540C" (1b);
- purple fabric "#4707 C2L C6 DWR 7645C" (1c);
- orange fabric "600D" (17);
- black leather "FIRARMINGO SOFT LEATHER" (2);
- black Velcro (4);
- black knitting "P2M 320 MESH/BLK" (3)



N. **3724080/E** date: 05/09/2018

article: "ADV S PANTS MEN" color black size M;

external side:

- black fabric "#4707 C2L C6 DWR" (1a);
- black leather "FIRARMINGO SOFT LEATHER" (2);

internal side:

- black felt "180G ALOVA AGAIST PEEING/BLK" (6);
- black perforated knitting "POLY 11:1 MESH" (8);
- black fabric "210T TAFFETA 4000 PU" (12);

removable lining:

- black fabric "210T TAFFETA P/D" (13);

main fastening system:

- by means of a metallic zipper and metallic button in contact with the user (40);

leg and ankle closure:

- metallic zipper;

external pockets:

- black fabric "210T TAFFETA P/D" (13) with metallic zip closure;

protectors pocket:

- for hip and knee pockets: black perforated knitting "POLY 11:1 MESH" (8) with Velcro; vents:
- black knitting "P2M 320 MESH/BLK" (3) with metallic zip closure;

article: "ADV S PANTS WOMEN" color black/grey/purple size S;

it differs from model "ADV S PANTS MEN" color black size M in the following features:

- black fabric "#4707 C2L C6 DWR" (1a);
- gray fabric "#4707 C2L C6 DWR 7540C" (1b);
- purple fabric "#4707 C2L C6 DWR 7645C" (1c);
- black leather "FIRARMINGO SOFT LEATHER" (2);

protectors inserted in the garment:

- shoulder protector
 - "SCL-2" company SAS TEC;
- elbow protector
 - "SCL-1" company SAS TEC;
- back protector
 - "SCL (X)* 19" company SAS TEC;
- knee and shin protector
 - "SCL-1" company SAS TEC;
- hip protector
 - "SC-1/77" company SAS TEC;



N. **3724080/E** date: 05/09/2018

The combinations for the impact abrasion tests:

A) 2+8 (zone 1-2-3);

B) 1+8 (zone 1-2-3);

C) 3 (vents, zone 3);

D) 1+1+8 (zone 1-2-3);

E) 1+12 (zone 2-3);

F) 2+12 (zone 2-3);

The seams externally identified in the garment ("SSS") are the followings ("//" means " stitched"):

- a) 1//2 Flat-seam, single stitching- with covered safety stitching (zone 1-2-3);
- b) 2//2 Flat-seam, single stitching- with covered safety stitching (zone 1-2-3);
- c) 1//1 Flat-seam, single stitching- with covered safety stitching (zone 2-3);

The seams identified in the protector pocket material are the followings ("//" means " stitched"):

- d) 8//8 Outside-seam, double stitching (protector pocket material);
- e) 8//9 Flat-seam "folded", single stitching (protector pocket material);
- f) 8//8 Flat-seam "folded", single stitching (protector pocket material);



N. **3724080/E**

| References | Tests | Measuring unit | Requirements | Results |
|---|---|-------------------|---|----------------------------------|
| EN ISO 13688:2013 | Protective clothing - general requirements | | | |
| 4.2 | Innocuousness | | Materials shall not adversely affect the health or hygiene of the user, materials shall not release substances generally know to be toxic, carcinogenic, mutagenic, allergenic, toxic to reproduction or otherwise harmful. | pass |
| 4.2/a UNI EN ISO 17075-1:2017# | Chromium VI (only leather) • Material 2 | mg/kg | ≤3 | < 3 |
| 4.2/c ISO 4045:2018 ISO 3071:2005 | pH - leather • Material 2 - other materials • Material 1a • Material 11 • Material 15 • Material 16 • Material 1b • Material 1c • Material 17 | | > 3,5 and < 9,5 | 3,90 7,2 6,5 6,2 6,5 7,0 7,0 7,1 |



N. **3724080/E**

date:

| References | Tests | Measuring unit | Requirements | Results |
|---|--|-------------------|------------------------|--|
| 4.2/d UNI EN ISO 7234-1:2015# leather UNI EN 4362-1:2017# textile | Azo colorants content: 1. 4-aminobiphenyl 2. Benzidine 3. 4-chloro-o-toluidine 4. 2-naphtylamine 5. 4-chloroaniline 6. 2,4-diaminoanisole 7. 4,4'diaminodiphenylmethane 8. 3-3'-dichloro benzidine 9. 3,3'-dimethoxy benzidine 10. 3,3'-dimethyl benzidine 11. 4,4'-methylenedi-o-toluidine 12. p-cresidine 13. 4,4'-mehylene-bis-(2-chloroaniline) 14. 4,4'-oxydianiline 15. 4,4'-thiodianiline 16. o-toluidine 17. 2,4-toluenediamine 18. 2,4,5-trimethylaniline 19. o-aminoazotoluene 20. 5-nitro-o-toluidine 21. 4-aminoazobenzene 22. o-anisidine 23. 2,4 xylidine 24. 2,6 xylidine * Under test conditions, 4-aminoazobenzene might break down into aniline and 1,4-Phenylenediamine. 92.3 mg/kg of aniline and 300.1 mg/kg of 1,4-Phenylenediamine were found in the present test sample. | mg/kg | absent (< 30 mg/kg) | material: 2 < 5 < 5 < 5 < 5 < 5 < 5 < 5 < 5 < 5 < 5 |
| 7234-2:2011# | colorants, which may release: 4-aminoazobenzene | mg/kg | < 30 | < 30 |



N. **3724080/E**

| References | Tests | Measuring unit | Requirements | R | esults |
|-----------------------|---|-------------------|--|----------|-------------|
| 4.2/d | Azo colorants content: | mg/kg | absent | | aterial: |
| UNI EN ISO | | | (< 30 mg/kg) | 1a+11+15 | 16+1b+1c+17 |
| 17234-1:2015# | 1. 4-aminobiphenyl | | | < 5 | < 5 |
| leather | 2. Benzidine | | | < 5 | < 5 |
| | 3. 4-chloro-o-toluidine | | | < 5 | < 5 |
| UNI EN | 4. 2-naphtylamine | | | < 5 | < 5 |
| 14362-1:2017# | 5. 4-chloroaniline | | | < 5 | < 5 |
| textile | 6. 2,4-diaminoanisole | | | < 5 | < 5 |
| | 7. 4,4'diaminodiphenylmethane | | | < 5 | < 5 |
| | 8. 3-3'-dichloro benzidine | | | < 5 | < 5 |
| | 9. 3,3'-dimethoxy benzidine | | | < 5 | < 5 |
| | 10. 3,3'-dimethyl benzidine | | | < 5 | < 5 |
| | 11. 4,4'-methylenedi-o-toluidine | | | < 5 | < 5 |
| | 12. p-cresidine | | | < 5 | < 5 |
| | 13. 4,4'-mehylene-bis-(2- | | | < 5 | < 5 |
| | chloroaniline) 14. 4,4'-oxydianiline | | | < 5 | < 5 |
| | 15. 4,4'-thiodianiline | | | < 5 | < 5 |
| | 16. o-toluidine | | | < 5 | < 5 |
| | 17. 2,4-toluenediamine | | | < 5 | < 5 |
| | 18. 2,4,5-trimethylaniline | | | < 5 | < 5 |
| | 19. o-aminoazotoluene | | | < 5 | < 5 |
| | 20. 5-nitro-o-toluidine | | | < 5 | < 5 |
| | 21. 4-aminoazobenzene | | | < 5 | < 5 |
| | 22. o-anisidine | | | < 5 | < 5 |
| | 23. 2,4 xylidine | | | < 5 | < 5 |
| | 24. 2,6 xylidine | | | < 5 | < 5 |
| 4.3 4.3.1- 4.3.2 - | Design | | The design should facilitate its correct | l | pass |
| 4.3.3 | | | positioning on the user and should ensure that it remains in place during the course of | | |
| | | | work, ensuring that no parts of the body get | | |
| | | | uncovered by expected movements by the wearer. When | | |
| | | | two or more items are worn together, they should be compatible. | | |



N. **3724080/E**

| References | Tests | Measuring unit | Requirements | Results |
|---------------------------------|--|-------------------|--------------|---------|
| 4.4 4.4.1 – 4.4.2 Annex C | Comfort Clothing: | | | |
| | - should provide a level of comfort consistent with the level of protection against hazard which is provided; | | pass | pass |
| | - should not have rough, sharp or hard surfaces that irritate or injure the user; | | pass | pass |
| | - should not be so tight, loose and/or heavy so that it restricts normal movements; | | pass | pass |
| | - should not be so tight that blood flow and deep breathing are restricted; | | pass | pass |
| | - allows the following movements: standing, sitting, walking, stair climbing, raising both hands above the head, bending over; | | pass | pass |
| | - should not be so loose that it flaps about or moves independently and inconveniently; | | pass | pass |
| | - should not be points at which unexpected and unintended gaps open up between or within components of the clothing; | | pass | pass |
| | - should not cause any unreasonable restriction of movement at any joint; | | pass | pass |
| | - putting on and removing other items of PPE should be possible without difficulty. | | pass | pass |



N. **3724080/E**

date:

| 4.4 | | unit | | Results |
|---------------|---|------|------|---------|
| | Comfort | | | |
| 4.4.1 – 4.4.2 | gradules eretabled and other | | | |
| Annex C | - armholes, crotch and other elements of clothing design are appropriately proportioned and positioned; | | pass | pass |
| | - the range of adjustment | | | |
| | available is adequate; | | pass | pass |
| | - arms and legs of the clothing should not be so long that they interfere with hand and foot | | pass | pass |
| | movements. | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |



N. **3724080/E**

| References | Tests | Measuring unit | Requirements | Results |
|---|--|-------------------|---|---|
| FprEN 17092- 3:2018 (FprEN 17092- 1:2018) (version 2018- 05) | Protective garments for motorcycle riders | | | |
| - | Class of protection - declared - verified | - | AAA, AA, A, B or C AAA, AA, A, B or C | AA AA |
| 4.1.1 (EN ISO 13688:2013 p. 4.2) | Innocuousness | - | Materials shall not adversely affect the health or hygiene of the user, materials shall not release substances generally know to be toxic, carcinogenic, mutagenic, allergenic, toxic to reproduction or otherwise harmful. | pass |
| 4.1.2 | Dimensional stability of garments | | | |
| (EN ISO 13688:2013 p. 5.2+5.3) | Dimensional changing due to cleaning | - | (5 washing cycles at 30°C) | washing procedure: 3G drying procedure: A |
| | Whole garment | | | |
| (ISO 5077:2007 ISO 6330:2012) | Domestic washing Jacket Measure a Measure b Measure c Measure d Measure e Measure f Measure g1/g2/g3 Measure h Measure i | % | ≥-5 and ≤+5 | 0 0 -0,5 -1,0 0 -0,5 -0,5/-0,5 0 |
| | Irouser Measure a Measure b Measure c Measure d Measure e Measure f Measure g | | | 0 -0,5 -0,5 -1,0 0 -0,5 -0,5 |



N. **3724080/E**

date:

| eferences | Tests | Measuring unit | Requirements | Results |
|-----------|---|-------------------|---|---------|
| - | After cleaning washing marking shall be legible | - | pass | pass |
| 4.1.3 | Garment and samples performance after cleaning | | | |
| - | General (not required for class B) | - | Garments and samples shall be cleaned according to EN ISO 13688:2013, 5.2 prior to testing and shall conform to the requirements specified in 4.2 to 4.8 of this standard after the required number of cleanings, if applicable | pass |
| | General (not required for class B) | - | For garments with removable mandatory or optional impact protectors, where according to the manufacturer's instructions the protectors are to be removed prior to cleaning, the protectors shall be able to be reinstalled after cleaning | pass |



N. **3724080/E**

date:

| References | Tests | Measuring unit | Requirements | Results |
|---|---|-------------------|--------------------------------------|--------------------------------|
| 4.2 | Impact energy absorption | | | |
| 4.2.1 (Table 1) (not required for class B) | Impact protection shall be present in the garment according to table 1 | - | pass | pass |
| , | For garments with pockets for optional impact protectors, there can be at least one type of impact protector that is available for each protector pocket; | - | pass | pass |
| | All impact protectors present in a garment, whether mandatory or optional, shall meet at least the Level 1 requirements according to the standards listed in Table 1. Pockets intended for impact protectors shall not contain any other items other than impact protectors complying with the applicable part of EN1621; | - | Pass | Pass |
| | EN 1621-1 protectors shall be positioned in the garment so that they cover the appropriate body part according to the relevant impact protector standard. This requirement applies also to optional protectors (EN 1621-2 and/or EN 1621-3) if present; | - | Pass | Pass |
| | Suit/Jackets: - Elbow (mandatory) - Shoulder (mandatory) - Chest (optional) - Back (optional) - Lumbar (optional) | - - - - | pass pass pass pass pass | pass pass - pass - |
| | Suits/Trousers: - Knee or knee leg (mandatory) - Hip (mandatory for Class AAA and AA, optional only Class A, B and C garments) | | pass pass | pass pass |



N. **3724080/E**

| References | Tests | Measuring unit | Requirements | Results |
|---------------------------------|--|-------------------|--------------|---------|
| 4.2.2 (5.5) (not required | Impact protector location and fixation | | | |
| for class B) | Internal or external impact protectors present in or on garments shall be correctly aligned in or on the garment no matter which system is used to hold them in place | - | pass | pass |
| | Garments, with impact protector pockets for location of optional impact protectors listed in the information notice for users, shall be manufactured to ensure correct positioning of the inserted impact protector EN 1621-1, EN 1621-2, prEN 1621-3, and EN 1621-4 protectors shall be positioned in the garment so that they cover the appropriate body part according to the relevant impact protector | - | pass | pass |
| | standard. Impact protectors shall be appropriately placed and restrained according to the test method described in prEN 17092-1:2017, 5.2.2 and 5.4.2. | - | pass | pass |



N. **3724080/E**

| References | Tests | Measuring unit | Requirements | Results |
|---|--|-------------------|--------------|---------|
| 4.2.2 (5.5) (not required for class B) | Restrain of impact protectors: The checks below shall be performed on a garment with protectors worn by an assessor; | | | |
| | a) A visual and tactile check is performed to confirm that protectors are over the correct location on the body also while performing the ergonomic exercises as in clause 5.5.4.3, Table 11, point 6; | - | pass | pass |
| | b) A visual and tactile check of the restraint of protectors in pockets is performed to confirm that the protectors are secure within the pockets; | - | pass | pass |
| | c) A visual and tactile check is performed to confirm that protectors restrained by other means are secured in their position; | - | pass | pass |
| 4.3 Table 2 (5.4) | Note; Results are reported in a specific table, at the end of the report. | - | - | - |



N. **3724080/E**

date:

| References | Tests | Measuring unit | Requirements | | Results | |
|--|---|-------------------|--------------|------|---------|------|
| 4.4 | Structurally strong seams | | | | | |
| 4.4.1 | - SSS in the SSL, which are on the exterior of the garment in Zone 1 and 2 shall have at least one line of the stitching protected by an SSL material | - | pass | | pass | |
| | - If present leather or textile abrasion overlays and reinforcements sewn onto the SSL shall have at least two rows of stitching attaching them to the SSL but are not required to have at least one line of stitching protected. | - | Pass | | - | |
| | - If present external rigid or semi- rigid reinforcements sewn into ("window stitched") or onto the SSL shall have at least two rows of stitching attaching them to the SSL but are not required to have at least one line of stitching protected. | - | pass | | - | |
| | | | | | seam: | |
| | | | | а | b | С |
| | Seam strength: - zone 1 | N/mm | ≥8 | 17,7 | 15,3 | - |
| o. 6.7 Annex B) | - zone 2 | | ≥8 | 17,7 | 15,3 | 18,3 |
| | - zone 3 | | ≥ 6 | 17,7 | 15,3 | 18,3 |
| | - protector pocket material (if present) | | ≥ 4 | - | - | - |
| | | | | | seam: | |
| 4.4.2 | Seam strength: | | | d | е | f |
| Table 3 EN 13594:2015 b. 6.7 Annex B) | - zone 1 | N/mm | ≥8 | - | - | - |
| ,, o., / \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \ | - zone 2 | | ≥8 | - | - | - |
| | - zone 3 | | ≥ 6 | - | - | - |
| | - protector pocket material (if present) | | ≥ 4 | 4,3 | 4,1 | 4,4 |



N. **3724080/E**

| References | Tests | Measuring unit | Requirements | Results |
|---------------------------|---|-------------------|--|-------------------------------|
| 4.6 | Restraint | | | |
| 4.6.2 (5.5.3.1) | Two-piece suit requirements for joint between upper part and lower part | | | |
| | Visually assess the garment and record whether any of the following has occurred: | | | |
| | a) failure of the connecting fastening system between the upper part and lower part | - | no | no |
| | b) gaps in protection anywhere between the upper part and the lower part | - | no | no |
| | The fastening system shall not be exposed and shall be protected by SSL material | - | pass | pass |
| 4.6.3 (5.5.3.2) | Garment sleeve restraint | - | shall not be possible to extract the test cone | pass |
| (5.5.3.2.4) | In the case of loop restraints, the distance between point A and point B shall not be more than 140 mm | - | pass | - |
| 4.7 | Additional garment construction requirements | | | |
| 4.7.1 | Garments shall meet the following requirements, according to their zones, which are determined according to the procedure described in clause 5.2 | - | pass | pass |
| 4.7.2 | Structural closures | | | |
| 4.4.2 | Seam strength of the structural | | | central closure of the jacket |
| Table 3 (EN 13594:2015 | closures: | | ≥8 | _ |
| p. 6.7 Annex B) | - zone 1 | N/mm | ≥8 | _ |
| | - zone 2 | | ≥ 6 | 16,9 |
| | - zone 3 | | 20 | |
| | Structural closures shall not separate anywhere along their length during testing | - | pass | pass |



N. **3724080/E**

date:

| References | Tests | Measuring unit | Requirements | Results |
|-----------------------------------|---|-------------------|--------------|-------------------------|
| | | | | external pocket closure |
| 4.4.2 Table 3 EN 13594:2015 | Seam strength of the structural closures: | | | |
| p. 6.7 Annex B) | - zone 1 | N/mm | ≥ 8 | - |
| | - zone 2 | | ≥8 | 10,0 |
| | - zone 3 | | ≥ 6 | 10,0 |
| | Structural closures shall not separate anywhere along their length during testing | - | pass | pass |
| | | | | sleeve and leg closure |
| 4.4.2 Table 3 EN 13594:2015 | Seam strength of the structural closures: | | | |
| b. 6.7 Annex B) | - zone 1 | N/mm | ≥8 | - |
| | - zone 2 | | ≥8 | 10,4 |
| | - zone 3 | | ≥ 6 | 10,4 |
| | Structural closures shall not separate anywhere along their length during testing | - | pass | pass |
| | | | | "vents" closure |
| 4.4.2 Table 3 EN 13594:2015 | Seam strength of the structural closures: | | | |
| b. 6.7 Annex B) | - zone 1 | N/mm | ≥8 | - |
| | - zone 2 | | ≥8 | - |
| | - zone 3 | | ≥ 6 | 8,3 |
| | Structural closures shall not separate anywhere along their length during testing | - | pass | pass |
| | | | | |
| | | | | |
| | | | | |
| | | | | |



N. **3724080/E**

| References | Tests | Measuring unit | Requirements | Results |
|------------------------------------|---|-------------------|--------------|-------------------------------------|
| | | | | connection between jacket and pants |
| 4.4.2 Table 3 (EN 13594:2015 | Seam strength of the structural closures: | | | |
| p. 6.7 Annex B) | - zone 1 | N/mm | ≥8 | - |
| | - zone 2 | | ≥8 | 13,0 |
| | - zone 3 | | ≥ 6 | 13,0 |
| | Structural closures shall not separate anywhere along their length during testing | - | pass | pass |
| | | | | central closure of the pants |
| 4.4.2 Table 3 (EN 13594:2015 | Seam strength of the structural closures: | | | |
| p. 6.7 Annex B) | - zone 1 | N/mm | ≥8 | - |
| | - zone 2 | | ≥8 | - |
| | - zone 3 | | ≥ 6 | 10,7 |
| | Structural closures shall not separate anywhere along their length during testing | - | pass | pass |



N. **3724080/E**

| References | Tests | Measuring unit | Requirements | Results |
|------------|---|-------------------|--------------|---------|
| 4.7.3 | Vents | | | |
| | Openings in any zone of the SSL created by vents or vent systems of any type, including vents closed with structural closures or vent systems designed with multiple closures or fastening systems used in combination to create a larger vent area, shall be completely covered by SSL material that meets the applicable zone requirements or the vent opening must be filled with material that meets the applicable zone requirements, with the exception of vents that are single linear openings in Zone 2 or single linear openings crossing from Zone 2 to Zone 3. These Vents may have an opening that is filled with Zone 3 material, provided the vent has been designed so that its opening is restricted to 4 cm or less in width, when measured at 90° to the line of the closure, at any point along the length of the vent. Apart from these exceptions, vents or vent systems crossing over more than one zone shall meet the requirements of the higher zone. | - | pass | pass |
| 4.7.4 | Pockets Pockets creating an opening in the SSL shall have SSL material inside which fills the exposed opening and extends along the interior of the pocket beyond the opening at least an additional 3 cm | - | pass | pass |



N. **3724080/E**

| References | Tests | Measuring unit | Requirements | Results |
|--------------------------|--|-------------------|--------------|---------|
| 4.8 (5.6) table 11 | Fit and ergonomics | | | |
| 1 a | Pre-donning assessment Can you confirm that no metallic, ceramic, plastic or similar hard materials present as studs, staples, rivets, plates, or other structures, used to form part of the protective layer of the garment, pose a hazard to the user? | - | yes/no | yes |
| b | Does the construction of the garment protect the body from such structures when necessary? | - | yes/no | yes |
| С | When such features do penetrate the protective layer, the inner surfaces of these features are flush to the protective layer? | - | yes/no | yes |
| d | Is the garment free from any rough, sharp or hard components, or other features that might cause irritation or that would make riding hazardous? | - | yes/no | yes |
| 2 | Is the garment sized in accordance with the manufacturer's fit information and in accordance with the fit instructions supplied in the manufacturer's information notice for users, or according to EN ISO 13688or is it made-to-measure? | - | yes/no | yes |
| 3 | | | | |
| а | Donning Is It possible to put on the garment and to operate the fasteners and adjusters without impediment? | - | yes/no | yes |
| b | Is it possible to don gloves and helmet while wearing the garment? | - | yes/no | yes |



N. **3724080/E**

date: 05/09/2018

| eferences | Tests | Measuring unit | Requirements | Results |
|-----------|--|-------------------|---|---------|
| 4 | Off-bike activities | | | |
| | Can the following be carried out without difficulty? | | | |
| а | Walking on the flat. | - | yes/no | yes |
| b | Mounting and dismounting a motorcycle or a device that mimics one. | - | yes/no | yes |
| | Riding actions | | | |
| 5 | Is it possible to perform the following without difficulty: | | | |
| а | Sit astride a motorcycle or device that mimics it, while adopting a riding position. | - | yes/no | yes |
| b | Make the body movements and position changes necessary to control the motorcycle. | - | yes/no | yes |
| С | While holding both handlebar grips, turn the head to look to the rear. | - | yes/no | yes |
| 6 | Are all impact protectors correctly positioned in such a way as to protect the appropriate body parts (refer to 5.4.2) whilst not preventing adequate movement of limbs or impeding the rider's effective control of the motorcycle? | - | yes/no | yes |
| 7 | Is the garment free of unnecessary tightness, which restricts body movement or blood flow in such a way as to prevent effective operation of the motorcycle? | - | yes/no | yes |
| 8 | Does the garment fit without creating dangerous interference with the helmet? | - | yes/no | yes |
| - | Size range the garment is sized in accordance with: | - | the manufacturer's fit information and in accordance with the fit instructions supplied in the information notice | pass |

End of the test report.